

Spring 4-3-2017

Preparation of High Strength Concrete using Meta-kaolin and Investigating its Freeze - Thaw Resistance

Vineeth Kanteti 3387428
SIUC, vineeth.kanteti@siu.edu

Follow this and additional works at: http://opensiuc.lib.siu.edu/esh_2017

Recommended Citation

Kanteti, Vineeth 3387428 "Preparation of High Strength Concrete using Meta-kaolin and Investigating its Freeze - Thaw Resistance." (Spring 2017).

This Article is brought to you for free and open access by the Emma Smith Hough Library Research Scholarship Awards at OpenSIUC. It has been accepted for inclusion in 2017 by an authorized administrator of OpenSIUC. For more information, please contact opensiuc@lib.siu.edu.

Preparation of High Strength Concrete using Meta-kaolin and Investigating its Freeze-Thaw Resistance

Sai Vineeth K (vineeth.kanteti@siu.edu), UGA, Dr. Prabir Kolay (pkolay@siu.edu), Ph.D., P.E., M.ASCE

Department of Civil and Environmental Engineering, SIUC

Abstract

The Worldwide consumption of concrete aggregates is approximately 11.5 billion tons per year for the construction of any infrastructures (Mehta and Monteiro, 2013). It has been predicted that more than 2.5 billion tons per year of coarse aggregates are expected to be consumed by the year 2020 for construction purposes (USGS, 2009). The raw material (i.e., coarse aggregate) used for concrete is becoming costly, depleting day by day, and its production uses a substantial amount of energy. Hence, the recycled aggregate (RA) provides the perfect solution for this growing problem. RA implementation would not only help in reducing landfill costs but also it stands as a eco-friendly solution to conserve natural virgin aggregates. Therefore, using these recycled aggregates presents a sustainable solution to the environmental impact at hand. Also, literature said that meta-kaolin is substance that can improve the strength of the concrete and more room than a natural aggregate consists is required for improved freeze-thaw resistance. For this, recycled aggregate has more voids and room inside for the water to expand when it melts inside. Hence, the current research foccuses on finding an optimum high strength concrete mix with an improved freeze-thaw resistance.

Methodology

- The standard test method for sieve analysis of fine and coarse aggregates determines the particle size distribution of fine and coarse aggregates by sieving.
- The standard test method for relative density and absorption of fine and coarse aggregate determine the specific gravity and absorption of the aggregates.
- The standard test method for resistance of coarse aggregate to degradation by abrasion determines the resistance to abrasion using the Micro-deval apparatus.
- Tests on freeze-thaw resistance of concrete include the relative dynamic modulus, weight loss and the length change tests.
- Slump test and air content tests are considered default when concrete was mixed initially. The air entrainment used was AEA PolychemVCR and super plasticizer was Melchem-M, both from GRT, Inc.
- The standard test method for compressive strength determine the compressible strength of the specimens such as molded cylinders and drilled cores. All the test methods were and will be performed based on various ASTM specifications as shown in the references section.

Problem Statement

To find the optimum concrete mix which includes meta-kaolin and air entrainment to check for increase in the freeze-thaw resistance and durability of the recycled aggregate concrete. Concrete is mixed with different percentages of meta-kaolin and air entrainment as a trail and error substitution.

Results and Discussions




Figure 1: Gradation curve of natural concrete aggregate. Figure 2: Gradation curve of recycled concrete aggregate. Figure 3: Gradation curve of natural fine aggregate.

Material	NCA	RCA	NFA
Relative Density (Specific gravity) (OD)	2.66	2.39	2.59
Relative Density (Specific Gravity) (SSD)	2.67	2.46	2.58
Apparent Relative Density (Specific gravity)	2.68	2.58	2.57
Absorption	0.33	2.93	0.68

Table 1: Absorption and specific gravity test results of natural coarse, recycled coarse and natural fine aggregates



Figure 4: Apparent Relative Density Test

Passing Sieve	Retained	Mass required (g)	NCA (g)	RCA (g)
19 mm	16 mm	375	375.743	375.437
16 mm	12.5 mm	375	375.423	375.654
12.5 mm	9.5 mm	750	749.064	752.149
Initial weight (g)		1500	1502.23	1503.24
Final weight (g)			1313.93	1233.83
Percentage loss			12.5	17.9

Figure 5: Before and After of the Micro-deval test. Table 2: Results of micro-deval test including percentage abrasion loss.




Table 3: Seven days compression test results - shows clear increase in strength of concrete due to meta-kaolin



Fig 6: Compression test of a cylindrical sample

Concrete Mix	Slump (in)	Slump with superplasticizer (in)	Air content (%)	Compressive strength (psi)	
				7 - days	14 - days
100% NCA + 0% RCA + 0% MK	2.9	4.5	7.5	1972.2	2709.41
100% NCA + 0% RCA + 5% MK	2.9	4.9	7.2	2177.19	2941.46
0% NCA + 100% RCA + 0% MK	3	4.6	7.2	1825.95	4/4/2017
0% NCA + 100% RCA + 5% MK	2.4	4.5	7.6	1857.1	4/5/2017

Figure 7: Freeze - Thaw Chamber in the laboratory. Table 4: Slump and Air - content of different concrete mixes

Conclusions

- The Particle size gradation of the fine aggregate has the least size of 0.075 mm and the maximum size of almost 4.75 mm; whereas, the natural and recycled coarse aggregate both have the least size of 1.18 mm and the maximum of 19 mm diameter.
 - The three different relative densities and absorption values of the fine, natural coarse and recycled coarse aggregates were found out and presented in the results and discussion section as shown. It can be seen that the recycled aggregate has a very high absorption value and a lower specific gravity than the natural aggregate.
 - According to the microdeval results, it is found that abrasion resistance of recycled aggregates is much weaker than that of the natural or virgin aggregates. The recycled coarse aggregate definitely has less density and more air content as compared to the natural aggregate which is required for the improved freeze-thaw resistance.
 - The compressive strength of the natural aggregates has increased by 9.5 % and that of the recycled aggregate has increased around 1.8% at seven days on the addition of 5% meta-kaolin. It's my hypothesis that this strength will increase with time and with a different percentage addition of meta-kaolin.
- Limitations: Due to several external factors including the shortage of time and recycled aggregate, this research couldn't be completed to its fullest and hence, the freeze-thaw tests and compression tests are still going on and will be completed by late summer this year.

References

- ASTM C127-15(2015), Standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate.
- ASTM C33-03(2003), Standard Specification for Concrete Aggregates.
- ASTM D6928-10 (2010), Standard Test Method for Resistance of Coarse Aggregate to Degradation by Abrasion in the Micro-Deval Apparatus.
- ASTM C88-99a (1999), Standard Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate.
- ASTM C39/C39M - 15a, Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens
- ASTM C128- 15, standard Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate.
- Mehta, P. K. and Paulo J. M. Monteiro (2013), Concrete: Microstructure, Properties, and Materials, McGraw Hill Publisher.
- Moses, A. (2013), Characterization and Utilization of Recycled Concrete Aggregates (RCA) for Road Pavement Work, M.S. Thesis, Southern Illinois University Carbondale, USA.
- Piotri Berkowski and Marta Kosior (2015), Effect of fiber on the concrete resistance to surface scaling due to cyclic freezing and thawing.
- Portland Cement Association, Concrete today (2012)
- USGS (2000), "Recycled Aggregates- Profitable Resource Conservation." USGS Fact Sheet FS- 181-99, Washington, DC: U.S. Geological Survey; <http://pubs.usgs.gov/fs/fs-0181-99>, accessed on March 31, 2012.

Acknowledgments

I sincerely thank CURCA, SIUC for providing me with such a wonderful opportunity and funding for the research work. This research couldn't develop into this stage without the guidance and support of Dr. Prabir Kolay all throughout the year. I thank you so much! To my life-coaches, my uncle Mehar, mother, Sandhya and father, Sreedhar: because I owe it all to you. Many Thanks!

Bibliography

- ASTM C117-13. "Standard Test Method for Materials Finer than 75- μm (No. 200) Sieve in Mineral Aggregates by Washing." *ASTM international*, 2013, Special Archives, Morris Library, SIUC.
- ASTM C127-15. "Standard Test Method for Relative Density (Specific Gravity) and Absorption of Coarse Aggregate." *ASTM international*, 2015, Special Archives, Morris Library, SIUC.
- ASTM C128-15. "Standard Test Method for Relative Density (Specific Gravity) and Absorption of Fine Aggregate." *ASTM international*, 2015, Special Archives, Morris Library, SIUC.
- ASTM C136 / C136M-14. "Standard Test Method for Sieve Analysis of Fine and Coarse Aggregates." *ASTM international*, 2014, Special Archives, Morris Library, SIUC.
- ASTM C138 / C138M-17. "Standard Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete." *ASTM international*, 2017, Special Archives, Morris Library, SIUC.
- ASTM C143 / C143M-15a. "Standard Test Method for Slump of Hydraulic-Cement Concrete." *ASTM international*, 2015, Special Archives, Morris Library, SIUC.
- ASTM C1611 / C1611M-14. "Standard Test Method for Slump Flow of Self-Consolidating Concrete." *ASTM international*, 2014, Special Archives, Morris Library, SIUC.
- ASTM C1645-16. "Standard Test Method for Freeze-thaw and De-icing Salt Durability of Solid Concrete Interlocking Paving Units." *ASTM international*, 2016, Special Archives, Morris Library, SIUC.
- ASTM C172 / C172M-14a. "Standard Practice for Sampling Freshly Mixed Concrete." *ASTM international*, 2014, Special Archives, Morris Library, SIUC.
- ASTM C173 / C173M-16. "Standard Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method." *ASTM international*, 2016, Special Archives, Morris Library, SIUC.
- ASTM C231 / C231M-17. "Standard Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method." *ASTM international*, 2017, Special Archives, Morris Library, SIUC.
- ASTM C39 / C39M-15a. "Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens." *ASTM international*, 2015, Special Archives, Morris Library, SIUC.
- ASTM C566-13. "Standard Test Method for Total Evaporable Moisture Content of Aggregate by Drying." *ASTM international*, 2013, Special Archives, Morris Library, SIUC.
- ASTM C666 / C666M-15. "Standard Test Method for Resistance of Concrete to Rapid Freezing and Thawing." *ASTM international*, 2015, Special Archives, Morris Library, SIUC.
- ASTM C70-13. "Standard Test Method for Surface Moisture in Fine Aggregate." *ASTM international*, 2013, Special Archives, Morris Library, SIUC.

- ASTM D6928-10. "Standard Test Method for Resistance of Coarse Aggregate to Degradation by Abrasion in the Micro-Deval Apparatus." *ASTM international*, 2010, Special Archives, Morris Library, SIUC.
- Berkowski, Piotr; Kosior-Kazberuk, Marta. "Effect of Fiber on the Concrete Resistance to Surface Scaling Due to Cyclic Freezing and Thawing." XXIV R-S-P seminar, Theoretical Foundation of Civil Engineering (24RSP) (TFoCE 2015), *Procedia Engineering*. 2015, pp. 121-127. Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- Donald J. Janssen, Mark B. Snyder. "Resistance of concrete to freezing and thawing." Strategic Highway Research Program, *National Research Council*. June 1994.
<http://onlinepubs.trb.org/onlinepubs/shrp/SHRP-C-391.pdf>.
- Gokce, A; Nagataki, S; Saeki, T; Hisada, M. "Freezing and thawing resistance of air-entrained concrete incorporating recycled coarse aggregate: the role of air content in demolished concrete." *Cement and Concrete Research*. pp. 799-806. 2004, Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- Huai-Shuai Shang; Ting-Hua Yi. "Freeze-Thaw Durability of Air-Entrained Concrete." *The Scientific World Journal*, Vol 2013, Hindawi Publishing Corporation. Database: Onesearch, Directory of Open Access Journals, Morris Library, SIUC.
- Jin, Mantong, *et al.* "Resistance of metakaolin-MSWI fly ash based geopolymer to acid and alkaline environments." *Journal of Non-Crystalline Solids*. 2016, pp. 116-122. Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- Kolay, P. K. and Moses, A. "Characterization and Utilization of Recycled Concrete Aggregate from Illinois as a Construction Material", American Society of Civil Engineers (ASCE), *Geotechnical Special Publication*, Feb 2014, pp. 3561-3570. Onesearch, Database: British Library Document Supply Morris Library Archives, SIUC.
- Matthew P. Adams. "Alkali-Silica Reaction in Concrete Containing Recycled Concrete Aggregates." *M.S. Thesis*. 2012.
<https://ir.library.oregonstate.edu/xmlui/bitstream/handle/1957/27864/AdamsMatthewP2012.pdf?sequence=1>.
- Medina, César, *et al.* "Freeze-thaw durability of recycled concrete containing ceramic aggregate." Special Volume: Sustainable consumption and production for Asia: Sustainability through green design and practice, *Journal of Cleaner Production*. February 2013, pp. 151-160. Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- Mehta, P. K. and Paulo J. M. Monteiro. *Concrete: Microstructure, Properties, and Materials*. McGraw Hill Publisher, 2013, Onesearch, Database: I-share, Morris Library, SIUC.
- Moses, A. "Characterization and Utilization of Recycled Concrete Aggregates (RCA) for Road Pavement Work." *M.S. Thesis*, Onesearch, Database: I-share, Morris Library, SIUC.

- Nabil M. Al-Akhras. "Performance of Glass Concrete Subjected to Freeze-Thaw Cycling." *The Open Construction and Building Technology Journal*. 2012, pp. 392-397. <https://benthamopen.com/contents/pdf/TOBCTJ/TOBCTJ-6-392.pdf>.
- Ohio Department of Transportation. "Soundness Test by Freeze/thaw." *Recycled Concrete materials report*, Database: Onesearch, I-share, Morris Library, SIUC.
- Portland Cement Association. "Freeze-thaw resistance." PCA, <http://www.cement.org/for-concrete-books-learning/concrete-technology/durability/freeze-thaw-resistance>.
- Rafat S. *Waste Materials and By-Products in Concrete*. Springer Publications, 2008.
- Richardson, A.E. *Strength and durability of concrete using recycled aggregates*. Handbook of recycled concrete and demolition waste. 2013, pp.330-348. Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- Richardson, David N.; Lusher, S. Michael. "Prediction of Freezing-and-Thawing Durability of Concrete." *ACI Materials Journal*, Vol. 112 Issue 3, pp. 439-449. May/Jun2015. Database: Onesearch, Morris Library, SIUC.
- Richardson, *et al.* "Freeze/thaw performance of concrete using granulated rubber crumbs." *Journal of Green buildings*, Vol. 6 number 1, 2010. http://www.collegepublishing.us/jgb/samples/JGB_V6N1_b03_Richardson.pdf.
- Shang, HS; Cao, WQ; Wang, B. "Effect of Fast Freeze-Thaw Cycles on Mechanical Properties of Ordinary-Air-Entrained Concrete." *Scientific World General*, 2014, Database: Onesearch, Science Citation Index, Morris Library, SIUC.
- Shang, Huaishuai, *et al.* "Behavior of air-entrained concrete after freeze-thaw cycles." *Acta Mechanica Solida Sinica*, 2009, pp. 261-266. Database: Onesearch, ScienceDirect, Morris Library, SIUC.
- State of California, Department of Transportation. "Guidelines for the design and inspection of concrete." *21st Century concrete guidelines*. April 2010. <http://www.dot.ca.gov/hq/esc/soe/section90/Guide-for-the-Design-and-Inspection-of-Concrete.pdf>.
- USGS. "Recycled Aggregates-Profitable Resource Conservation." *USGS Fact Sheet FS- 181-99*, DC: U.S. Geological Survey. <http://pubs.usgs.gov/fs/fs-0181-99>.
- Zhang, Peng, Li, Qing-Fu. "Freezing–thawing durability of fly ash concrete composites containing silica fume and polypropylene fiber." *Proceedings of the Institution of Mechanical Engineers, Part L - Journal of Materials: Design & Applications*, Sage Publications, Ltd. Vol. 228 Issue 3, Jul2014, pp. 241-246. Database: Onesearch, Science Citation Index, Morris Library, SIUC.